



Data Sheet for:

EPDM Rubber Sheetting KG-300

Gaskets Grade KG-300 is a general-purpose commercial EPDM. Highly resistant to Ozone, Weathering, and Water. Widely used in pipeline gaskets. Also available in grades suitable for Food and Potable Water.

Properties	Test Method	Value
Base Polymer	SBR/EPDM	
Hardness	ASTM D2240 00	65° SHORE 'A'
Tensile Strength	ASTM D412	3 MPa
Specific Gravity	ASTM D792	1.5 g/cm ³
Elongation @ Break	ASTM D412	250% min
Min Continuous Working Temp		-20° C
Max Continuous Working Temp		70° C
Max Intermittent Working Temp		90° C
Compression Set (70° for 22 Hours)	ASTM D395 METHOD B	30% Max

General Guidelines for Use

Abrasion Resistance	Moderate
General Purpose	Not Recommended
Food Use	Not Recommended
Ozone Weather Resistance	Moderate
Flame Retardancy	Not Recommended
Electrical Resistance	Not Recommended

Disclaimer: While care has been taken to ensure the information contained in this publication is correct, Oliver Ashworth Limited accepts no responsibility or liability for information found to be misleading. Technical information has been supplied by our supply chain partners. It is the responsibility of the end-user to ensure that the products used are suitable for their intended application.

**Ashworth, Mill Hill Street, Bolton, Greater Manchester, BL2 2AB,
Tel: 0161 967 0400**

Enquiries@Ashworth.uk.com

Technical.services@Ashworth.uk.com